



# Prep PE/PP

### Product

Simson Prep PE/PP is a one-step pretreatment for the improvement of the adhesion of several specific Simson Silyl Modified Polymer based products to plastic substrates. Consult the Technical Data Sheet of the particular product.

### Applications

- Pretreatment of plastics, in particular PE and PP.

### Features

- Fast drying; approximately 15 minutes.
- Easy to use one-step process.
- Efficient in use.

### Method of use

The substrates should be clean, dry and free of dust and grease. Keep the packaging well closed until the moment of use. Do not use Prep PE/PP direct from the original packaging. Pour as much Prep PE/PP in a clean glass or tin as can be used within 30 minutes and immediately close the original tin firmly. Prep PE/PP should be applied in a not too thick a coat by means of a brush or a lint free cloth. After a drying time of approximately 15 minutes the sealant or adhesive can be applied. Best results are obtained when the bonding/sealing will be realised within 4 hours after applying Prep PE/PP. Therefore do not apply more Prep PE/PP than can be sealed within 4 hours. Avoid contact with the pretreated surface, because this can affect the adhesion negatively.

## ADHESIVES AND SEALANTS

# Prep PE/PP

### Technical data

Dry contents	ca. 2.5%
Specific gravity	0.87 g/ml
Flashpoint	+25°C
Drying time	±15 minutes
Colour	transparent
Packaging	500 ml tin

### Coverage

The coverage of Prep PE/PP is approximately 15 m<sup>2</sup> per liter.

### Storage stability

Prep PE/PP can be stored for 12 months in an original, unopened container in a dry place at temperatures between +5°C and +30°C.

### Further information

The following publication is available on request:

- Material Safety Data Sheets (MSDS)

#### UK

Bostik Ltd.  
Stafford  
Tel: +44 (0) 1785 27 27 27  
Fax: +44 (0) 1785 22 26 65

#### France

Bostik S.A.  
Paris  
Tel: +33 (0) 1 74 96 91 18  
Fax: +33 (0) 1 47 96 94 20

#### Germany

Bostik GmbH  
Borgholzhausen  
Tel: +49 (0) 54 25/8 01-0  
Fax: +49 (0) 54 25/80 11 40

#### The Netherlands

Bostik B.V.  
's-Hertogenbosch  
Tel: +31 (0) 73 6 244 244  
Fax: +31 (0) 73 6 244 344

For more Bostik locations please consult [www.bostik.com](http://www.bostik.com)

**Bostik**  
The Adhesive Company

All figures, recommendations and safety precautions are based on thorough investigations and our actual experience and are without engagement. Although the documentation has been set up with most carefulness, we do not accept any responsibility for mistakes, inaccuracies or printer's errors. We reserve the right to adjust the product, whenever we feel necessary. Because the design, the quality of the substrate and the conditions during application fall beyond our control, no responsibility for executed works can be accepted on the basis of this documentation. We therefore recommend to carry out own tests on the spot. All our sales and deliveries are subject to our general sales- and delivery conditions.